

## DSS Pro 14oz Blockout

DSS Pro 14 oz. Blockout is a two sided blockout banner material that is smooth and printable on both sides. The refined scrim pattern and dual print surfaces of the DSS Pro were engineered for print professionals seeking a media with an as large as possible color gamut at high speeds with low ink consumption. DSS Pro has a low curl formula that is ideal for rollup banner stands, POP and any indoor hanging graphics. DSS Pro is available in widths ranging from 39" to 80" in standard lengths of 164' and 750' (250yards). This product is compatible with eco solvent, solvent, latex and UV inks.

### Material Details

CHARACTERISTICS	TEST METHOD	METRIC	ENGLISH
Support Cloth	DIN ISO 2076	Polyester	Polyester
Yarn dtex	DIN 53830	150 x 150 dtex	150 x 150 denier
Type of Coating	N/A	PVC	PVC
Total Weight	DIN EN ISO 2286-2	460 g/m <sup>2</sup>	13.5 oz/yd <sup>2</sup>
Tensile Strength	ISO 13934-1:1999 C.R.E. STRIP METHOD	549.4 x 475.0 N/5cm	62.7 X 54.2 lbs/in
Tear Strength (warp/weft)	ISO 13937-2:2000 C.R.E. SINGLE TONGUE METHOD	13.3 x 6.1 N	2.97 X 1.4 lbs
Adhesion Strength (warp/weft)	ISO 2411:1991 C.R.E.	4.1 x 4.1 N/5cm	4.68 x 4.68 lbs/in
Flame Resistance	DIN 75200	NFPA-701, Title 19	
Low Temperature (No Crack at:)	ISO 13934:1999	Low at -20°C	Low at -4°F
RF Weldable (Heat Sealable)	DIN 53354	Yes	Yes
Fungus Resistant	ASTM G21	Yes	

### Applications

	POP	Banner	Banner Stands	Block-out	Tradeshaw Graphics	Display Systems	Indoor Banners
Applications	■	■	■	■	■	■	■

### Ink Printability

Solvent	Eco Solvent	UV	Latex	Screen Printing	Dye Transfer	Dye Direct
■	□	■	■*	■		

### Available Sizes

Metric (m)	English (inches)
0.99, 1.37, 1.60, 1.88, 2.03	39, 54, 63, 74, 80

Key: ■ - Excellent □ - Good

\* one side only

The information on physical and chemical characteristics is based upon tests believed to be reliable. The values are intended only as a source of information. A legally binding guarantee of specific properties is not to be inferred from our specifications. They are given without guaranty and do not constitute a warranty. The purchaser should independently determine, prior to use, the suitability of this material for his/her specific purpose. (Data represents averages and is not intended for use as a specification.)

#### Distributed by:

**ATLANTA**  
800-241-6049  
678-602-4140  
FAX: 678-602-4139

**BOSTON**  
781-749-4590  
FAX: 781-740-2866

**CHICAGO**  
800-654-1357  
630-543-4600  
FAX: 630-543-0856

**DALLAS**  
800-338-2241  
817-477-4770  
FAX: 817-473-4515

**LOS ANGELES**  
800-825-4846  
909-923-1879  
FAX: 909-923-4079

**MIAMI**  
800-432-5068  
954-971-0436  
FAX: 954-971-9218

**NEW YORK/NEWARK**  
973-589-7800  
212-962-6565  
FAX: 973-589-3225

**PHILADELPHIA**  
800-222-0146  
856-662-3373  
215-462-3636  
FAX: 856-486-4552

**TORONTO**  
888-460-4406  
905-953-9393  
FAX: 905-953-1331