



## Q4001B Streakless Ultra Matte Coating

Aqueous Coating Technical Data Sheet

The Prisco Q4001B is a "Streakless" Ultra Matte coating for inline application wet trapping over lithographic inks to both sides of the substrate. It is designed to produce an even, fast drying, streak free film over a wide variety of substrates and inks. This allows for quick turnaround times and an even defect-free surface.

### Advantages:

- Superior Ultra Matte finish
- Great leveling with a streak free surface
- Minimizes burnishing and marring
- Good Rub Resistance
- Can be over-coated with:
  - UV coatings
  - Oleo resinous varnishes
  - Aqueous coatings
- Displays adhesion to:
  - Plastic film laminates,
  - Hot foil stamping,
  - Glue
  - Laser imprinting

### Physical Properties:

Viscosity	17-19 seconds, #3 EZ Zahn timed @ 25°C/77°F
pH	7.5-8.5
Gloss	10-20
Solids	38% +/-3%
Wt./gal	8.6-8.8 lbs/gal
Block Resistance	Pass 120°F, 10PSI, 6 Hrs
Rub Resistance	Good @ 200+ Sutherland Rubs w/ 4lb weight

### Application:

Commercial Sheetfed  
 General Purpose  
 Folding Carton

- **Application Viscosity**-Stir and use as received.
  - Viscosity reduction only with Prisco technical support
  - Recommended Application Temperature 70-80°F
- **Equipment**-Blanket and tower coaters, anilox coaters
- **Drying**-Sufficient volumes or warm dry air, and medium and short wave IR. Pile temperatures should range 95-100°F 1<sup>st</sup> side, and 85-90°F 2<sup>nd</sup> side
- **Wet Film Weight**-Recommend 0.8-1.2 wet pounds per 1000 square feet of substrate
- **Inks**-Sheetfed lithographic oxidative ink. Wax content should be limited to 2-3% polyethylene.
- **Clean up**-Cleaning is best before coating dries. Use warm water and Prisco Aqueous Coating Cleaner
- **Shelf Life**-6 months stored at room temperature.

**Product Code:** RR43-55B (55 gallon drum), RR43-30B (30 gallon drum), RR43-5GF (5 gallon pail)

Prisco recommends that you test coatings for specialty applications using the actual raw materials to be used in production prior to printing.

Read MSDS before using this product

## An ISO 9001:2008 Registered Facility

**PRINTERS' SERVICE**  
 26 Blanchard Street  
 Newark, New Jersey 07105  
 (212) 962-6565 • (973) 589-7800  
 FAX (973) 589-3225  
 www.prisco.com

**ATLANTA**  
 800-241-6049  
 404-876-1234  
 FAX: 404-873-2917

**CHICAGO**  
 800-654-1357  
 630-543-4600  
 FAX: 630-543-0856

**LOS ANGELES**  
 800-825-4846  
 909-923-1879  
 FAX: 909-923-4079

**NEW YORK/NEWARK**  
 973-589-7800  
 212-962-6565  
 FAX: 973-589-3225

**PRISCO CANADA  
 TORONTO**  
 888-460-4406  
 905-953-9393  
 FAX: 905-953-1331

**BOSTON**  
 781-749-4590  
 FAX: 781-740-2866

**DALLAS**  
 800-338-2241  
 817-477-4770  
 FAX: 817-473-4515

**MIAMI**  
 800-432-5068  
 954-385-1975  
 FAX: 954-385-8875

**PHILADELPHIA**  
 800-222-0146  
 856-662-3373  
 215-462-3636  
 FAX: 856-486-4552

**PRISCO EUROPE (U.K.)**  
 44(0)1423 810 320  
 FAX: 44(0)1423 810 319  
**PRISCO EUROPE (Continent)**  
 32(0)56 42 35 76  
 32(0)56 42 35 97



## Product Bulletin

