



**Q6503A Matte Non-Curl Light Weight Paper Coating**  
Aqueous Coating Technical Data Sheet



**Product Bulletin**

The Prisco Q6503A is a Matte work & turn coating for inline application wet trapping over lithographic inks to both sides of the substrate. It is designed to produce an even and fast drying film formation over a wide variety of substrates and inks. This allows for quick turnaround times and an even defect-free surface. This coating is specially designed for use on lightweight paper to minimize or eliminate sheet curl, fanning, and fit register problems.



**Advantages:**

- Excellent Matte Finish
- Non Curl
- Good Rub Resistance
- Can be over-coated with:
  - UV coatings
  - Oleo resinous varnishes
  - Aqueous coatings
- Displays adhesion to:
  - Plastic film laminates
  - Hot foil stamping
  - Glue
  - Laser imprinting

**Physical Properties:**

Viscosity	14-16 seconds, #3 EZ Zahn timed @ 25°C/77°F
pH	7.5-8.5
Gloss	10-20
Solids	42% +/-2%
Wt./gal	8.6-8.8 lbs/gal
Block Resistance	Pass 120°F, 10PSI, 6 Hrs
Rub Resistance	Good @ 200+ Sutherland Rubs w/ 4lb weight

**Application:**

Commercial Sheetfed  
General Purpose

- **Application Viscosity**-Stir and use as received.
  - Viscosity reduction only with Prisco technical support
  - Recommended Application Temperature 70-80°F
- **Equipment**-Blanket and tower coaters, anilox coaters
- **Drying**-Sufficient volumes or warm dry air, and medium and short wave IR. Pile temperatures should range 95-100°F 1<sup>st</sup> side, and 85-90°F 2<sup>nd</sup> side
- **Wet Film Weight**-Recommend 0.8-1.2 wet pounds per 1000 square feet of substrate
- **Inks**-Sheetfed lithographic oxidative ink. Wax content should be limited to 2-3% polyethylene.
- **Clean up**-Cleaning is best before coating dries. Use warm water and Prisco Aqueous Coating Cleaner
- **Shelf Life**-6 months stored at room temperature.

**Product Code:** RS65-55B (55 gallon drum), RS65-30B (30 gallon drum), RS65-5GF (5 gallon pail)

Prisco recommends that you test coatings for specialty applications using the actual raw materials to be used in production prior to printing.

Read MSDS before using this product

an ISO 9001:2008 Registered Facility

**PRINTERS' SERVICE**  
26 Blanchard Street  
Newark, New Jersey 07105  
(212) 962-6565 • (973) 589-7800  
FAX (973) 589-3225  
www.prisco.com

**ATLANTA**  
800-241-6049  
404-876-1234  
FAX: 404-873-2917

**CHICAGO**  
800-654-1357  
630-543-4600  
FAX: 630-543-0856

**LOS ANGELES**  
800-825-4846  
909-923-1879  
FAX: 909-923-4079

**NEW YORK/NEWARK**  
973-589-7800  
212-962-6565  
FAX: 973-589-3225

**PRISCO CANADA**  
**TORONTO**  
888-460-4406  
905-953-9393  
FAX: 905-953-1331

**BOSTON**  
781-749-4590  
FAX: 781-740-2866

**DALLAS**  
800-338-2241  
817-477-4770  
FAX: 817-473-4515

**MIAMI**  
800-432-5068  
954-385-1975  
FAX: 954-385-8875

**PHILADELPHIA**  
800-222-0146  
856-662-3373  
215-462-3636  
FAX: 856-486-4552

**PRISCO EUROPE (U.K.)**  
44(0)1423 810 320  
FAX: 44(0)1423 810 319  
**PRISCO EUROPE (Continent)**  
32(0)56 42 35 76  
32(0)56 42 35 97