



E-Cure 704 General Purpose Gloss Flexo UV Coating
 Ultraviolet Coating Technical Data Sheet

The Prisco E-Cure 704 General Purpose Flexo UV Coating is designed for application on a variety of substrates including non absorbent and synthetic. The product is designed for in line application with Flexo Presses and Flexo type coaters. It is selected for its combined features of excellent UV gloss, non-yellowing film, excellent flexibility, and fast cure response. This allows for quick turnaround times and an even defect-free surface. This product is designed to have excellent adhesion properties, flow and wetting characteristics, gloss depth and clarity.

Advantages:

- Excellent Gloss and flexibility
- Non Yellowing
- Fast Cure response
- Low VOC

Physical Properties:

Viscosity	18-22 seconds, #3 EZ Zahn timed @ 25°C/77°F 110-150 CPS, Brookfield LV Viscometer @ 25°C/77°F
Gloss	>90
Wt./gal	9.3 lbs/gal
Cure	100 fpm, 200 wpi American UV Mini Conveyor* *Note-tested in controlled lab conditions
MEK Rubs	15-20 Double Rubs

Application:

Flexo

- **Application Viscosity**-Stir and use as received.
 - Recommended Application Temperature 70-80°F
- **Equipment**-Blanket and tower coaters, anilox coaters
- **Curing**-Sufficient amount of focused UV energy depending on press, press speed, and dryer capability
- **Inks**-UV/Co-Cure, primed or oxidized conventional ink
- **Clean up**-Prisco UV Cleaner
- **Shelf Life**-6 months stored at room temperature

Product Code: RE74-55A (55 gallon drum), RE74-30A (30 gallon drum), RE74-5GF (5 gallon pail), RE74-1GQ (1 gallon pail)

Prisco recommends that you test coatings for specialty applications using the actual raw materials to be used in production prior to printing.

Read MSDS before using this product

an ISO 9001:2008 Registered Facility



Product Bulletin



PRINTERS' SERVICE
 26 Blanchard Street
 Newark, New Jersey 07105
 (212) 962-6565 • (973) 589-7800
 FAX (973) 589-3225
 www.prisco.com

ATLANTA
 800-241-6049
 404-876-1234
 FAX: 404-873-2917

CHICAGO
 800-654-1357
 630-543-4600
 FAX: 630-543-0856

LOS ANGELES
 800-825-4846
 909-923-1879
 FAX: 909-923-4079

NEW YORK/NEWARK
 973-589-7800
 212-962-6565
 FAX: 973-589-3225

**PRISCO CANADA
 TORONTO**
 888-460-4406
 905-953-9393
 FAX: 905-953-1331

BOSTON
 781-749-4590
 FAX: 781-740-2866

DALLAS
 800-338-2241
 817-477-4770
 FAX: 817-473-4515

MIAMI
 800-432-5068
 954-385-1975
 FAX: 954-385-8875

PHILADELPHIA
 800-222-0146
 856-662-3373
 215-462-3636
 FAX: 856-486-4552

PRISCO EUROPE (U.K.)
 44(0)1423 810 320
 FAX: 44(0)1423 810 319
PRISCO EUROPE (Continent)
 32(0)56 42 35 76
 32(0)56 42 35 97