Prisco[®] E-Cure 159-FC General Purpose Gloss UV Coating

UV Coating Technical Data Sheet

The Prisco E-Cure 159-FC is a high gloss UV coating for inline or offline application over a variety of inks and substrates. It is designed to produce an even and fast curing film formation with a superior gloss finish. This allows for quick turnaround times and an even defect-free surface. This product is designed to have excellent flexibility, adhesion properties, and gloss depth and clarity. This product is a faster cure version of the E-Cure 159.

>90

9.3 lbs/gal

Advantages:

- Superior gloss levels
- Fast Cure Response
- Good Rub and Taber Resistance
- Non-Yellowing
- Low VOC
- Low Viscosity

Physical Properties:

Viscosity

Gloss Wt./gal Cure

MEK Rubs

Application:

Sheetfed Flexo

- Application Viscosity-Stir and use as received.
 - Recommended Application Temperature 70-80°F
- Equipment-Blanket and tower coaters, anilox coaters
- · Curing-Sufficient amount of focused UV energy depending on press, press speed, and dryer capability

15-20 Double Rubs

- Inks-UV/Co-Cure, primed or oxidized conventional sheetfed
- Clean up-Prisco UV Cleaner
- Shelf Life-6 months stored at room temperature.

Product Code: RH33-55A (55 gallon drum), RH33-30A (30 gallon drum), RH33-5GF (5 gallon pail)

Prisco recommends that you test coatings for specialty applications using the actual raw materials to be used in production prior to printing.

14-18 seconds, #3 EZ Zahn timed @ 25°C/77°F 70-110 cps, Brookfield LV Viscometer @ 25°C/77°F

100 fpm, 200 wpi American UV Mini Convevor*

*Note-tested in controlled lab conditions

Read MSDS before using this product

an ISO 9001:2008 Registered Facility

PRINTERS' SERVICE

26 Blanchard Street Newark, New Jersey 07105 (212) 962-6565 • (973) 589-7800 FAX (973) 589-3225 www.prisco.com

BOSTON 781-749-4590 FAX: 781-740-2866 CHICAGO 800-654-1357 630-543-4600 FAX: 630-543-0856

DALLAS 800-338-2241 817-477-4770 FAX: 817-473-4515 LOS ANGELES 800-825-4846 909-923-1879 FAX: 909-923-4079

MIAMI 800-432-5068 954-385-1975 FAX: 954-385-8875 NEW YORK/NEWARK 973-589-7800 212-962-6565 FAX: 973-589-3225

PHILADELPHIA 800-222-0146 856-662-3373 215-462-3636 FAX: 856-486-4552 PRISCO CANADA TORONTO 888-460-4406 905-953-9393 FAX: 905-953-1331

PRISCO EUROPE (U.K.) 44(0)1423 810 320 FAX: 44(0)1423 810 319 PRISCO EUROPE (Continent) 32(0)56 42 35 76 32(0)56 42 35 97

Product Bulletin



404-876-1234 FAX: 404-873-2917

ATLANTA 800-241-6049 404-876-1234