



26 Blanchard Street | Newark NJ 07105 | (973) 589-7800 | www.prisco.com

# PRISCO® E-Cure H-UV-870 Satin H-UV Coating

# **Product Description:**

The Prisco E-Cure H-UV-870 is a satin H-UV coating for inline application over H-UV inks and a variety of substrates. It is designed to produce an even and fast curing film formation with a superior satin finish. This allows for quick turnaround times and an even defect-free surface. This product is designed to have excellent flexibility and adhesion properties. The E-Cure H-UV-870 has been field tested and approved on the H-UV Komori press. It has good cure response with minimal to no surface tack. Results may vary depending H-UV system.

# Advantages:

- Superior Satin Finish, excellent flexibility and scratch resistance
- Good cure response, Excellent rub and Taber resistance
- Low odor, low VOC, non-yellowing

# **Physical Properties:**

•	Viscosity (cps)	300-400 cps, Brookfield LV Viscometer @ 25°C/77°F
•	Viscosity (seconds)	_38-48 seconds #3 Zahn Cup @ 25°C/77°F
•	Gloss	30-45
•	Wt./gal	_9.3 lbs/gal
•	Cure	H-UV "D" Bulb, High @ 100 fpm (tested in controlled lab conditions w/
	UVEXS Cure Unit)	
	MFK Rubs	15-25 Double Rub

### Application (Sheetfed and Flexo)

- Application Viscosity Stir well. Keep covered and reduce light exposure when using.
- Equipment Blanket and tower coaters, anilox coaters
- Curing Sufficient amount of focused H-UV energy depending on press, press speed, and energy capability.
- Inks H-UV Ink, primed or oxidized conventional sheetfed inks.
- Clean Up Prisco UV Cleaner
- Shelf Life 6 months stored at room temperature. Keep away from heat >100°F and minimize the products exposure to light.

#### READ SDS BEFORE USING THIS PRODUCT **Product Code:**

RI81-55A (55 gallon drum), RI81-30A (30 gallon drum), RI81-5GB (5 gallon pail), RI81-ACT (275 gallon Tote)

Prisco recommends that you test coatings for specialty applications using the actual raw materials to be used in production prior to printing.



Atlanta **Support:** 678-601-4140 Orders: 800-241-6049

Newark **Support:** 973-589-7800 Orders: 800-222-0146

**Boston** 781-749-4590 800-222-0146 Philadelphia

800-222-0146

856-662-3373

Chicago 630-543-4600 800-241-6049

+32 56 40 41 82

817-477-4770 800-241-6049

**United Kingdom** +32 56 40 41 82

Los Angeles 909-923-1879 800-825-4846

905-953-9393 888-460-4406

Miami 954-971-0436 800-241-6049

61 2 4702 1211