



PRISCO® E-Cure H-UV-880 Matte H-UV Coating

Product Description:

The Prisco E-Cure H-UV-880 is a Matte H-UV coating for inline application over H-UV inks and a variety of substrates. It is designed to produce an even and fast curing film formation with a superior matte finish. This allows for quick turnaround times and an even defect-free surface. This product is designed to have excellent flexibility and adhesion properties. The E-Cure H-UV-880 has been field tested and approved on the H-UV Komori press. It has good cure response with minimal to no surface tack. Results may vary depending H-UV system.

Advantages:

- Superior Matte Finish, excellent flexibility and scratch resistance
- Good cure response, Excellent rub and Taber resistance
- Low odor, low VOC, non-yellowing

Physical Properties:

- Viscosity (cps) _____ 500-600 cps, Brookfield LV Viscometer @ 25°C/77°F
- Viscosity (seconds) _____ 58-70 seconds #3 Zahn Cup @ 25°C/77°F
- Gloss _____ 10-30
- Wt./gal _____ 9.3 lbs/gal
- Cure _____ H-UV "D" Bulb, High @ 100 fpm (tested in controlled lab conditions w/ UVEXS Cure Unit)
- MEK Rubs _____ 15-25 Double Rub

Application (Sheetfed and Flexo)

- Application Viscosity - Stir well. Keep covered and reduce light exposure when using.
- Equipment - Blanket and tower coaters, anilox coaters
- Curing - Sufficient amount of focused H-UV energy depending on press, press speed, and energy capability.
- Inks – H-UV Ink, primed or oxidized conventional sheetfed inks.
- Clean Up - Prisco UV Cleaner
- Shelf Life - 6 months stored at room temperature. Keep away from heat >100°F and minimize the products exposure to light.

Product Code:

READ SDS BEFORE USING THIS PRODUCT

RI87-55A (55 gallon drum), RI87-30A (30 gallon drum), RI87-5GB (5 gallon pail), RI87-ACT (275 gallon Tote)

Prisco recommends that you test coatings for specialty applications using the actual raw materials to be used in production prior to printing.



Atlanta
Support: 678-601-4140
Orders: 800-241-6049

Boston
781-749-4590
800-222-0146

Chicago
630-543-4600
800-241-6049

Dallas
817-477-4770
800-241-6049

Los Angeles
909-923-1879
800-825-4846

Miami
954-971-0436
800-241-6049

Newark
Support: 973-589-7800
Orders: 800-222-0146

Philadelphia
856-662-3373
800-222-0146

Belgium
+32 56 40 41 82

United Kingdom
+32 56 40 41 82

Toronto
905-953-9393
888-460-4406

Australia
61 2 4702 1211