



## Q6757C-XF Grease Resistant Coating

### Product Description:

Prisco Q6757C-XF is a general purpose gloss coating for inline application wet trapping over lithographic inks to the front or back side of C1S substrate. It can also be applied over flexographic inks and substrates in packaging and carton applications. It is designed to produce an even and fast drying film formation and is grease resistant. Multiple applications of this product may be required for desired resistance characteristics. This product is compliant to FDA CFR 176.170, 176.180.

### Advantages:

- Grease Resistant passes 3M Kit Test # 10, Good Rub Resistance
- Average gloss levels, FDA CFR 176.170, 176.180

### Physical Properties:

- Viscosity (seconds) ----- 20-22 seconds, #3 EZ Zahn times @ 25°C/77°F
- pH ----- 8.5-9.5
- Solids ----- 40% +/-2%
- Wt/Gal.----- 8.6-8.8 lbs/gal
- Block Resistance ----- Pass 120°F, 10PSI, 6 Hrs
- Rub Resistance ----- Good @ 200+ Sutherland Rubs w/ 4lb weight

### Application (Commercial, Flexo, Sheetfed, Folding Carton)

- Application Viscosity - stir and use as received (application temperature = 70-80°F)
- Equipment - Blanket and tower coaters, anilox coaters
- Drying - Sufficient volumes or warm dry air, and medium and short wave IR. Pile temperatures should range 95-100°F 1st side, and 85-90°F 2nd side.
- Wet Film Weight - Recommend 1.0-1.2 wet pounds per 1000 square feet of substrate. Multiple applications may be required to achieve desired grease resistance.
- Inks - Sheetfed lithographic oxidative ink. Wax content should be limited to 2-3% polyethylene
- Clean up - Best before coating dries. Use warm water and Prisco Aqueous Coating Cleaner
- Shelf Life - 6 months stored at room temperature

### Product Code: **READ SDS BEFORE USING THIS PRODUCT**

RY04-55B (55-gal. drum), RY04-30B (30-gal. drum), RY04-5GF (5-gal. pail)

Prisco recommends that you test coatings for specialty applications using the actual raw materials to be used in production prior to printing.

1809



**Atlanta**  
Support: 678-601-4140  
Orders: 800-241-6049

**Boston**  
781-749-4590  
800-222-0146

**Chicago**  
630-543-4600  
800-241-6049

**Dallas**  
817-477-4770  
800-241-6049

**Los Angeles**  
909-923-1879  
800-825-4846

**Miami**  
954-971-0436  
800-241-6049

**Newark**  
Support: 973-589-7800  
Orders: 800-222-0146

**Philadelphia**  
856-662-3373  
800-222-0146

**Belgium**  
+32 56 40 41 82

**United Kingdom**  
+32 56 40 41 82

**Toronto**  
905-953-9393  
888-460-4406

**Australia**  
61 2 4702 1211